

RECEIVED
CENTRAL FAX CENTER

SEP 17 2007

IN THE CLAIMS:

Please amend the claims as follows:

1. (currently amended) A method for decorating and installing a cementitious substrate, the method comprising:

selecting a base color scheme for a substrate plurality of substrates formed of a cementitious material;

selecting an accent color scheme;

providing the substrate plurality of substrates, each having the base color scheme and a top surface, the top surface having an exposed portion and a covered portion;

applying before curing, onto [[a]] the exposed portion of the top surface of the substrate each substrate of the plurality of substrates, a substantially random distribution of medallions of a cementitious material as accents, colored in the accent color scheme, the distribution being substantially random among substrates of the plurality of substrates;

curing together the each substrate and the corresponding medallions, leaving the medallions bonded onto the top surface and extending above the top surface; and

installing the plurality of substrates, after curing, as a roof covering with the exposed portions of some of the plurality of substrates overlapping the covered portions of others of the plurality of substrates.

2. (currently amended) The method of claim 1, further comprising texturing the top surface of each substrate to produce a substantially random pattern before applying the accent medallions.

3. (currently amended) The method of claim 1 wherein ~~the~~ each substrate comprises cement and aggregate having a comparatively low to zero slump.

4. (currently amended) The method of claim 1 wherein ~~the~~ each substrate comprises cement and aggregate having substantially zero slump.

5. (currently amended) The method of claim 1 wherein ~~the~~ each substrate contains at least two colors of substantially the same cementitious material.

6. (currently amended) The method of claim 1 wherein the materials forming the base color scheme are mixed comparatively finely to form color variegations within substantially each ~~piece~~ of the substrate.

7. (currently amended) The method of claim 1 further comprising mixing the materials in the base color scheme comparatively grossly to provide variegation primarily from ~~piece-to-piece~~ of the substrate to substrate within the plurality of substrates.

8. (original) The method of claim 1 further comprising providing a base color scheme having at least one color distinct from the accent color scheme.

9. (original) The method of claim 1 further comprising selecting a base color scheme having at least two colors distinct from each other.

10. (original) The method of claim 1 further comprising selecting a base color scheme having at least one color corresponding to a neutral hue and corresponding to natural stone.

11. (currently amended) The method of claim 1 further comprising selecting an accent color scheme having at least one color distinct from the base color scheme of the substrate.

12. (original) The method of claim 1 further comprising selecting a base color scheme having at least one color corresponding to a natural aging event.

13. (original) The method of claim 1 further comprising selecting an accent color scheme having at least one color distinct from the base color scheme.

14. (original) The method of claim 1 further comprising selecting an accent color scheme having at least two colors distinct from colors of the base color scheme.

15-16. (canceled)

17. (original) The method of claim 1 further comprising selecting the base color scheme by selecting colors corresponding to moss and lichens.

18. (original) The method of claim 1 further comprising selecting the accent color scheme by selecting colors substantially corresponding to naturally occurring colors of biota.

19. (currently amended) The method of claim 1 further comprising selecting the accent color scheme by selecting colors substantially corresponding to naturally occurring hues of biota local to the location of use of the substrate of installing.

20. (original) The method of claim 1 further comprising selecting the accent color scheme by selecting colors corresponding to moss and lichens.

21. (original) The method of claim 1 further comprising selecting an accent color scheme by selecting colors naturally occurring as a result of mineral deposits in stone.

22. (original) The method of claim 1 wherein the medallions are formulated of a cementitious material containing cement, water, and aggregate.

23. (original) The method of claim 22 wherein the proportions of constituents within the accent medallion are in the range of from about one part cement for about four parts aggregate to about one part cement for about 0.25 parts aggregate.

24. (original) The method of claim 23 wherein the proportion of cement to aggregate is substantially one part cement for about two parts aggregate.

25. (original) The method of claim 24 wherein the cement is Portland cement.

26. (original) The method of claim 24 wherein the aggregate is sand.

27. (original) The method of claim 26 wherein the sand is masonry sand.

28. (original) The method of claim 22, wherein the cementitious material further comprises from about five percent to about twenty-five percent pigment.

29. (original) The method of claim 22 wherein the cementitious material further comprises from about five percent to about twenty-five percent water.

30. (original) The method of claim 22 wherein the amount of aggregate is selected to provide substantially zero slump in the cementitious material.

31. (original) The method of claim 22 where in the ratio of cement to aggregate is in a ratio of from about 0.25 to about four.

32. (original) The method of claim 31 wherein the ratio of cement to aggregate is in a ratio of from about 0.25 to about two.

33. (original) The method of claim 32 wherein the ratio of cement to aggregate is about 0.5.

34. (currently amended) The method of claim 1 wherein the medallions are applied within from about one second to about thirty minutes after formation of the each substrate.

35. (currently amended) The method of claim 34 wherein the medallions are applied within a time from about one second to about twenty minutes after formation of the each substrate.

36. (currently amended) The method of claim 35 wherein the medallions are applied within a time from about one second to about ten minutes after formation of the each substrate.

37. (currently amended) The method of claim 36 wherein the medallions are applied within a time from about one second to about less than eight minutes after formation of the each substrate.

38. (currently amended) The method of claim 37 wherein the medallions are applied within a time from about one second to about less than two minutes after formation of the each substrate.

39. (currently amended) The method of claim 1 wherein the medallions are applied within a time selected to provide fully integrated cohesion between the medallions and the each substrate.

40. (currently amended) The method of claim 1 wherein the medallions are applied within a time selected to provide substantially integrated cohesion between the medallions and the each substrate.

41. (currently amended) The method of claim 1 wherein the medallions are formed of a cementitious material having a liquid content selected to provide a previously determined depth of elevation variation between ~~the~~ each substrate and the medallion.

42. (original) The method of claim 41 wherein the depth corresponds substantially to the texture of biota.

43. (currently amended) The method of claim 42 wherein the depth corresponds to biota corresponding to a location of ~~application of the substrate~~ installing.

44. (currently amended) The method of claim 1, further comprising texturing the top surface of each substrate in a pattern having a substantially random orientation selected from the group consisting of linear, arcuate, angular, and a combination thereof.

45. (currently amended) The method of claim 44 wherein the random orientation forms an acute angle with a longitudinal direction of ~~the substrate~~ a substrate of the plurality of substrates.

46. (currently amended) The method of claim 44 wherein the random orientation forms an obtuse angle with respect to a longitudinal direction of ~~the substrate~~ a substrate of the plurality of substrates.

47. (original) The method of claim 44 wherein the random orientation forms a combination of two or more of a linear pattern, arcuate pattern, and angular pattern.

48. (currently amended) The method of claim 44 wherein at least one of the direction and accent color scheme is selected by a producer of ~~the substrate~~ a substrate of the plurality of substrates.

49. (currently amended) The method of claim 44 wherein at least one of the direction and accent color scheme is selected by the designer of ~~the substrate~~ a substrate of the plurality of substrates.

50. (currently amended) The method of claim 44 wherein at least one of the direction and accent color scheme is selected by the architect responsible for ~~a structure on which the substrate is to be applied~~ the roof covering.

51. (currently amended) The method of claim 44 wherein at least one of the direction and accent color scheme is selected by a user of the ~~substrate~~ plurality of substrates.

52. (currently amended) The method of claim 44 wherein texturing comprises manually brushing ~~the substrate~~ a substrate of the plurality of substrates.

53. (currently amended) The method of claim 44 wherein texturing comprises automatically and mechanically brushing ~~the substrate~~ a substrate of the plurality of substrates by a mechanical device.

54. (original) The method of claim 1, wherein at least one color in the base color scheme corresponds to at least one of carbonate deposits, lime deposits, soil deposits, weathered cement, weathered aggregate, iron oxide deposits, metal oxide deposits, biota propagation, and chemical reaction of another color of material in the base color scheme.

55. (original) The method of claim 54 wherein the biota propagated are selected from at least one of moss, lichens, algae, and fungi.

56. (original) The method of claim 1 wherein at least one color in the accent color scheme is selected to correspond to substantially a color selected from the group consisting of carbonate deposits, lime deposits, soil deposits, dust deposits, weathered aggregate, weathered cement, metal oxide, a local mineral, a chemical reaction of a base material, and biota propagation.

57. (original) The method of claim 56 wherein the biota propagated are selected from moss, lichens, fungi, algae, plants, symbiotic pairs of organisms, and symbiotic groups of organisms.

58. (original) The method of claim 56 wherein the biota are selected from an advanced, developed, slowly growing organism.

59. (currently amended) The method of claim 58 wherein the biota are selected from organisms local to the location of ~~use of the substrate~~ installing.

60. (original) The method of claim 1 wherein the accent color scheme corresponds to at least one of the group consisting of pale green, dark green, brown, yellowish brown, yellow, iridescent green, greenish black, and black.

61. (new) A method comprising:

providing a plurality of roofing tiles formed of an uncured cementitious material, each tile of the plurality of roofing tiles having a top surface comprising an exposed portion and a covered portion;

selecting an accent color scheme;

applying onto the exposed portion of each tile before curing, a distribution of medallions of a cementitious material as accents, colored in the accent color scheme, the distribution being applied to each tile in a substantially random arrangement, the distribution for each tile differing substantially randomly from the distribution of the other tiles of the plurality of roofing tiles;

curing each tile and the corresponding medallions, leaving the medallions bonded onto the top surface and extending above the top surface; and

installing the plurality of roofing tiles, after curing, on a roof with the exposed portions of some of the plurality of roofing tiles overlapping the covered portions of others of the plurality of roofing tiles.

62. (new) A method comprising:

molding a plurality of roofing tiles in an uncured cementitious material, each tile of the plurality of roofing tile including a top surface comprising an exposed portion and a covered portion;

selecting an accent color scheme;

throwing onto the exposed portion of each tile before curing, a substantially random distribution of medallions of a cementitious material as accents, colored in the accent color scheme;

curing each tile and the corresponding medallions, leaving the medallions bonded onto the top surface and extending above the top surface; and

installing the plurality of roofing tiles, after curing, on a roof with the exposed portions thereof cumulatively presenting a substantially random distribution of medallions and with the exposed portions of some of the plurality of roofing tiles overlapping the covered portions of others of the plurality of roofing tiles.